



Case Study: Furniture

eTables

Industry:
Furniture


Location:
Brooklyn, NY

Architect:
Brave Space

Materials Used:

Brave Space Design in Brooklyn, NY uses Plyboo edge grain amber and natural plywood for their Third Round table great for keeping your things nearby but out of sight!

Pictured here is a close-up of the beautifully eclectic mix of grain-patterns visible along the edges.



Amber Edge Grain
Bamboo Plywood
BP-V019A-NAUF/FSC



Natural Edge Grain
Bamboo Plywood
BP-V019N-NAUF/FSC



Specifications

Possible LEED Credits:

Low emitting materials and certified wood

Physical / Mechanical Properties - Edge Grain Bamboo Plywood

Dimensions:	3/4" x 48" x 96" 19mm x 1219mm x 2438mm (*mm tolerance +/- .5mm thickness)
Construction:	Three-ply, cross core construction.
Working with Plyboo:	A worksheet is provided with each panel containing useful tips and information and is also available on our website at plyboo.com/downloads .
ASTM E84: Surface Burning	Class C
ASTM D1037: Dimensional Stability	<ul style="list-style-type: none"> • Linear Expansion (3-ply): Parallel -0.04% / Perpendicular -0.07% • Thickness Swell (3-ply): -0.13% Screw Hold (3-ply) (face/back/edge) <ul style="list-style-type: none"> • 742 lbs/ 831 lbs/ 860 lbs average
ASTM D4442: Moisture Content	6-9% average
ASTM D 6007-02: Formaldehyde Concentration in Air from Wood Products, small chamber test	Plyboo = 0.004 ppm (surpasses CARB II standards, 0.05ppm & ULEF standards of 0.04ppm)

Physical / Mechanical Properties - Flat Grain Bamboo Plywood

Dimensions:	3/4" x 48" x 96" 19mm x 1219mm x 2438mm (*mm tolerance +/- .5mm thickness)
Construction:	Three-ply, cross core construction.
Working with Plyboo:	A worksheet is provided with each panel containing useful tips and information and is also available on our website at plyboo.com/downloads .
ASTM E84: Surface Burning	Class C
ASTM D1037: Dimensional Stability	<ul style="list-style-type: none"> • Linear Expansion (3-ply): Parallel -0.04% / Perpendicular -0.07% • Thickness Swell (3-ply): -0.13% Screw Hold (3-ply) (face/back/edge) <ul style="list-style-type: none"> • 742 lbs/ 831 lbs/ 860 lbs average
ASTM D4442: Moisture Content	6-9% average
ASTM D 6007-02: Formaldehyde Concentration in Air from Wood Products, small chamber test	Plyboo = 0.004 ppm (surpasses CARB II standards, 0.05ppm & ULEF standards of 0.04ppm)